

# TEST 144/3 serial number: 05

polyester/cotton, 65/35, soiled with make-up

**generally:**

<b>according:</b>	Swissatest soiling with lipstick/make-up
<b>suitable:</b>	sensitive to the amount of detergent, to temperature and to lipase
<b>date of production:</b>	Sep 2010
<b>durability:</b>	September 2024 ( reviewed in September 2023 )
<b>storing conditions:</b>	must be well packed and kept in the dark

**specification of base material:**

<b>article 213</b>	polyester/cotton fabric, 65/35, bleached, without opt. brightener
<b>thread count in cm</b>	warp: 23.5 weft: 25
<b>yarn count in Nm</b>	warp: 34 weft: 34
<b>weight in g/m<sup>2</sup></b>	155.0
<b>width in cm</b>	147.0
<b>Y-value</b>	90.9
<b>Rem<sub>460nm</sub></b>	88.4

**specification of soiled fabric:**

<b>soiling</b>	one side printed with make-up make-up: mixture of fatty components, and pigment amount of make-up: about 2 g/m <sup>2</sup>
<b>weight in g/m<sup>2</sup></b>	160.0
<b>width in cm</b>	25.0
<b>Y-value</b>	74.7
<b>Rem<sub>460nm</sub></b>	63.6

**measuring conditions:**

instrument	DC800V (spectrophotometer)
illuminant / observer	D65 / 10°
measuring geometry	d/8°
wavelength range	420 to 750nm
filter	UV barrier at 420nm
measuring diameter	26 mm
gloss	excluded