

TEST 222 serial number: 15

cotton fabric, cretonne, raw, unbleached

generally:

according:	Swissatest unsoiled test fabrics
suitable:	base material, load, and so on
date of production:	June 2014
durability:	June 2034
storing conditions:	must be well packed and kept dark

specification of base material:

article 222	cotton fabric, cretonne, raw, unbleached
thread count in cm	warp: 34 weft: 20
yarn count in Tex	warp: 30 weft: 50
weight in g/m2	205.0
width in cm	177.0
Y-value	68.3
Rem460nm	28.9

measuring conditions:

instrument	DC800V (spectrophotometer)
illuminant / observer	D65 / 10°
measuring geometry	d/8°
wavelength range	420 to 750nm
filter	UV barrier at 420nm
measuring diameter	26 mm
gloss	excluded

