

# TEST 210 serial number: 1527

cotton fabric, plain, bleached, w/o optical brightener

generally:

<b>according:</b>	Swissatest unsoiled test fabrics
<b>suitable:</b>	base material, load, and so on
<b>date of production:</b>	Feb 2014
<b>durability:</b>	Feb 2034
<b>storing conditions:</b>	must be well packed and kept dark

specification of base material:

<b>article 210</b>	cotton fabric, plain weave, bleached, without optical brightener
<b>thread count in cm</b>	warp: 24 weft: 24
<b>yarn count in Tex</b>	warp: 36 weft: 36
<b>weight in g/m<sup>2</sup></b>	180
<b>width in cm</b>	169
<b>Y-value</b>	89.8
<b>Rem<sub>460nm</sub></b>	85.9

**measuring conditions:**

instrument	DC800V (spectrophotometer)
illuminant / observer	D65 / 10°
measuring geometry	d/8°
wavelength range	420 to 750nm
filter	UV barrier at 420nm
measuring diameter	26 mm
gloss	excluded