

# TEST 220 serial number: 01

cotton/polyester twill, 50/50, bleached

generally:

<b>according:</b>	Swissatest unsoiled test fabrics
<b>suitable:</b>	base material, load, and so on
<b>date of production:</b>	June 2014
<b>durability:</b>	June 2024
<b>storing conditions:</b>	must be well packed and kept dark

specification of base material:

<b>article 220</b>	cotton/polyester twill, 50/50, bleached, w/o optical brightener
<b>thread count in cm</b>	warp: 45 weft: 32
<b>yarn count in Nm</b>	warp: 34 weft: 34
<b>weight in g/m<sup>2</sup></b>	240.0
<b>width in cm</b>	150.0
<b>Y-value</b>	87.6
<b>Rem460nm</b>	83.2

**measuring conditions:**

instrument	DC800V (spectrophotometer)
illuminant / observer	D65 / 10°
measuring geometry	d/8°
wavelength range	420 to 750nm
filter	UV barrier at 420nm
measuring diameter	26 mm
gloss	excluded